## LITECORE

## LITECOREPANELS.COM





\*Building photos are meant to demonstrate stone appearance and may not necessarily be taken from Litecore™ projects.

\*Computer generated images and printed reproductions may not accurately match natural stone colors.

## ROCHERONS DORÉ CLAIR<sup>™</sup> -FRENCH LIMESTONE LIMESTONE

The dense, compact grain structure of this limestone gives it a marble-like quality in its appearance. A uniform, rosy beige background provides a neutral base for occasional small shell inclusions. A resilient and versatile choice for any interior or exterior application.

PHYSICAL TEST RESULTS		IMPERIAL	METRIC
Absorption by weight	ASTM C97	0.40%	0.40%
Density	ASTM C97	166.87 lb/ft <sup>3</sup>	2 673.1 kg/m <sup>3</sup>
Compressive strength	ASTM C170	24 275 Psi	167.37 MPa
Modulus of rupture	ASTM C99	2 310 Psi	15.92 MPa

**QUARRY LOCATION** Comblanchien, Bourgogne, France



## LITECORE